

OCT 23 2006

Application No.: 10/091080

Case No.: 57080US002

AMENDMENT TO THE CLAIMS:

The following list of claims will replace all prior versions of claims in the application:

1. (currently amended) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive slurry comprising
superabrasive particles;
a continuous phase comprising a reactive curing binder precursor; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater than 500, an Amine Value, and an AV of greater than 4.5, wherein $AV = 1000 * [(Amine\ Value) / (Mw)]$, wherein a majority of the superabrasive particles are dispersed as individual particles.
2. (original) The abrasive article of claim 1 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight (Mw) of greater than 1000.
3. (original) The abrasive article of claim 1 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight (Mw) of between about 3000 and about 4000.
4. (original) The abrasive article of claim 3 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having an AV of between about 5 and about 7.5.
5. (original) The abrasive article of claim 1 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight (Mw) of between about 8000 and about 9000.

Application No.: 10/091080

Case No.: 57080US002

6. (original) The abrasive article of claim 5 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having an AV of between about 12 and about 13.
7. (original) The abrasive article of claim 1 wherein the abrasive coating comprises at least about 30% by weight of a superabrasive particle.
8. (original) The abrasive article of claim 7 wherein the abrasive coating comprises between about 30% by weight and about 80% by weight of a superabrasive particle.
9. (canceled)
10. (previously presented) The abrasive article of claim 1 wherein the abrasive coating comprises a binder.
11. (original) The abrasive article of claim 1 wherein the superabrasive particle is diamond.
12. (original) The abrasive article of claim 11 wherein the diamond has a particle size less than 2 micrometers.
13. (currently amended) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive slurry comprising
superabrasive particles;
a continuous phase comprising a reactive curing binder precursor ; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater than 10,000, an Amine Value, and an AV of greater than 1.0, wherein $AV=1000*[(Amine$

Best Available Copy

Application No.: 10/091080

Case No.: 57080US002

Value)/(Mw)], wherein a majority of the superabrasive particles are dispersed as individual particles.

14. (currently amended) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive slurry comprising
superabrasive particles;
a continuous phase comprising a reactive curing binder precursor; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater than 100,000, an Amine Value, and an AV of greater than 0, wherein $AV = 1000 * [(Amine\ Value) / (Mw)]$, wherein a majority of the superabrasive particles are dispersed as individual particles.
15. (original) The abrasive article of claim 14 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight (Mw) of greater than 150,000.
16. (currently amended) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive slurry comprising
superabrasive particles;
a continuous phase comprising a reactive curing binder precursor; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater than 500 and a measurable total Amine Value, wherein a majority of the superabrasive particles are dispersed as individual particles.

Application No.: 10/091080

Case No.: 57080US002

17. (currently amended) A method of manufacturing an abrasive article comprising coating an abrasive slurry comprising superabrasive particles, a continuous phase comprising a reactive curing binder precursor, and a dispersant comprising a polymer having an average molecular weight (Mw) of greater than 500, an Amine Value, and an AV of greater than 4.5 onto a backing, wherein $AV=1000*[(\text{Amine Value})/(\text{Mw})]$, wherein the superabrasive particles comprise at least 20% dry weight of all solids in the slurry, and wherein a majority of the superabrasive particles are dispersed as individual particles; and solidifying the abrasive slurry.
18. (original) The method of claim 17 wherein the abrasive slurry is cured.
19. (currently amended) An abrasive article comprising a backing having a major surface; and an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive slurry comprising
superabrasive particles;
a continuous phase comprising a reactive curing binder precursor; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater than 500, an Amine Value, and an AV of greater than 4.5, wherein $AV=1000*[(\text{Amine Value})/(\text{Mw})]$, wherein a majority of the superabrasive particles are dispersed as individual particles.
20. (new) The abrasive article of claim 1 wherein the abrasive slurry remains opaque for at least five minutes if sonicated for at least 25 seconds.
21. (new) The abrasive article of claim 1 wherein the abrasive slurry does not settle to form a cake in less than 30 minutes if sonicated for at least 20 seconds.

Application No.: 10/091080

Case No.: 57080US002

22. (new) The abrasive article of claim 1 wherein the superabrasive particles have a nominal size, the abrasive slurry has a particle size distribution, and at least 78.4 percent of the particles in the particle size distribution are less than 1.5 times the nominal size of the superabrasive particles.

Best Available Copy